

M. A. R. V. Properties  
of  
Synteen Geogrids

Property	Symbol	Method	<b>SF20</b>	
Note: All geogrids woven PET with PVC Coatings				
<b>Tensile Properties</b>			LBS/FT	
MD - Ultimate Strength	Tult	ASTM D-4595	1940	
MD - Ultimate Strain at Failure	%	ASTM D-4595	14.4%	
MD - Creep Reduced Strength	TI	ASTM D-5262	1259	
<b>DESIGN STRENGTH PROPERTIES</b>				
CREEP Reduction Factor(ed=10'	RFCR	AASHTO 98	1.54	
AGING/DURABILITY Reduction Factor 5<soil PH<8	RFD	AASHTO 98	1.15	
INSTALLATION DAMAGE Reduction Factor 1:100mm Max, 30mm D50, PI<6	RFID	AASHTO 98	1.73	
2:20mm Max, 0.7mm D50, PI<6	RFID	AASHTO 98	1.1	
3:20mm Max, .1-.5mmD50, PI<20	RFID	AASHTO 98	1.1	
Tult / RF for Soil Type 1: =	LTDS	ASHTO 98	633	
Tult / RF for Soil Type 2: =	LTDS	AASHTO 98	995	
Tult / RF for Soil Type 3: =	LTDS	AASHTO 98	995	
<b>DESIGN INTERACTION PROPERTIES</b>			Note: Ci & Cds te	
Coefficient of Interaction:	Ci	GRI - GG5 '91	Ci	
Coefficient of Direct Sliding:	Cds	ASTM D-5321	Cds	
Soil Type 1:		see above	0.75	0.7
Soil Type 2:		see above	0.8	0.8
Soil Type 3:		see above	0.7	0.75
<b>PHYSICAL PROPERTIES</b>			US	
MD - Aperture Size:	(ins.)	measured	0.75	
CMD - Aperture Size:	(ins.)	measured	0.75	
Synteen can custom produce roll size and vary aperture size for site specific applications				